



1-800-773-0062  
www.marianinc.com

# Adhesive Transfer Tapes with Adhesive 300

927 • 950 • 950EK • 9458 • 9471 • 9471PC • 9472 • 9671 •  
9672 • 9673 • 9674

## Technical Data

March 2016

**Product Description** 3M™ Adhesive Transfer Tapes with 3M™ Adhesive 300 offer excellent adhesion to a wide variety of surfaces, including low surface energy plastics and foam. This pressure sensitive medium firm acrylic adhesive family features very high initial adhesion with good holding power and is available in several thicknesses and a variety of liner configurations to help ensure excellent process flexibility.

### Construction Information



| Product                           | Adhesive Thickness     | Liner Type<br>Liner Thickness                  | Liner Color                                |
|-----------------------------------|------------------------|--|--|
| 3M™ Adhesive Transfer Tape 927    | 2.0 mils<br>(0.05 mm)  | 60# Densified Kraft<br>3.5 mils<br>(0.09 mm)   | Tan, No Print                              |
| 3M™ Adhesive Transfer Tape 950    | 5.0 mils<br>(0.13 mm)  | 60# Densified Kraft<br>3.5 mils<br>(0.09 mm)   | Tan, No Print                              |
| 3M™ Adhesive Transfer Tape 950EK  | 5.0 mils<br>(0.13 mm)  | 78# Extensible Kraft,<br>5.7 mils<br>(0.13 mm) | White, No Print                            |
| 3M™ Adhesive Transfer Tape 9458   | 1.0 mils<br>(0.025 mm) | 55# Densified Kraft,<br>3.2 mils<br>(0.08 mm)  | White, No Print                            |
| 3M™ Adhesive Transfer Tape 9471   | 2.0 mils<br>(0.05 mm)  | 60# Densified Kraft,<br>3.5 mils<br>(0.09 mm)  | Tan, Green Print<br>"Hi Strength Adhesive" |
| 3M™ Adhesive Transfer Tape 9471PC | 2.0 mils<br>(0.05 mm)  | 60# Polycoated Kraft,<br>4.5 mils<br>(0.11 mm) | Tan, No Print                              |
| 3M™ Adhesive Transfer Tape 9472   | 5.0 mils<br>(0.13 mm)  | 60# Densified Kraft<br>3.5 mils<br>(0.09 mm)   | Tan, Green Print<br>"Hi Strength Adhesive" |
| 3M™ Adhesive Transfer Tape 9671   | 2.0 mils<br>(0.05 mm)  | 83# Polycoated Kraft,<br>6.0 mils<br>(0.15 mm) | Tan, Green Print<br>"Laminating Adhesive"  |
| 3M™ Adhesive Transfer Tape 9672   | 5.0 mils<br>(0.13 mm)  | 83# Polycoated Kraft,<br>6.0 mils<br>(0.15 mm) | Tan, Green Print<br>"Laminating Adhesive"  |
| 3M™ Adhesive Transfer Tape 9673   | 2.0 mils<br>(0.05 mm)  | 83# Polycoated Kraft,<br>6.0 mils<br>(0.15 mm) | Tan, No Print                              |
| 3M™ Adhesive Transfer Tape 9674   | 5.0 mils<br>(0.13 mm)  | 83# Polycoated Kraft,<br>6.0 mils<br>(0.15 mm) | Tan, No Print                              |

**Note:** The thickness listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc. While past data pages have listed nominal thicknesses, the coat weight (and theoretical caliper) has not changed.

# 3M™ Adhesive Transfer Tapes with Adhesive 300

927 • 950 • 950EK • 9458 • 9471 • 9471PC • 9472 • 9671 • 9672 • 9673 • 9674

## Typical Physical Properties and Performance Characteristics

90° Peel Adhesion @ RT: ASTM D-3330 (Modified)  
2 mil Aluminum Foil Backer

| Substrate       | Product                             | 15 min dwell @ RT      | 72 hr dwell @ RT       |
|-----------------|-------------------------------------|------------------------|------------------------|
| Stainless Steel | 9458                                | 42 oz/in<br>12 N/25 mm | 50 oz/in<br>14 N/25 mm |
|                 | 927,<br>9741, 9741PC,<br>9671, 9673 | 52 oz/in<br>14 N/25 mm | 59 oz/in<br>16 N/25 mm |
|                 | 950, 950EK, 9472,<br>9672, 9674     | 74 oz/in<br>20 N/25 mm | 86 oz/in<br>24 N/25 mm |
| ABS             | 9458                                | 30 oz/in<br>8 N/25 mm  | 30 oz/in<br>8 N/25 mm  |
|                 | 927,<br>9741, 9741PC,<br>9671, 9673 | 31 oz/in<br>8 N/25 mm  | 34 oz/in<br>9 N/25 mm  |
|                 | 950, 950EK, 9472,<br>9672, 9674     | 34 oz/in<br>9 N/25 mm  | 40 oz/in<br>11 N/25 mm |
| Polypropylene   | 9458                                | 31 oz/in<br>8 N/25 mm  | 41 oz/in<br>11 N/25 mm |
|                 | 927,<br>9741, 9741PC,<br>9671, 9673 | 45 oz/in<br>12 N/25 mm | 52 oz/in<br>14 N/25 mm |
|                 | 950, 950EK, 9472,<br>9672, 9674     | 60 oz/in<br>16 N/25 mm | 62 oz/in<br>17 N/25 mm |

# 3M™ Adhesive Transfer Tapes with Adhesive 300

927 • 950 • 950EK • 9458 • 9471 • 9471PC • 9472 • 9671 • 9672 • 9673 • 9674

---

## Environmental Performance

**Humidity Resistance** – High humidity has a minimal effect on adhesive performance. Bond strength (is generally higher/shows no significant reduction) after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

**UV Resistance** – When properly applied, nameplates and decorative trim parts are not adversely affected by outdoor exposure.

**Water Resistance** – Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength (increases/is maintained).

**Temperature Cycling Resistance** – High bond strength (is maintained /increases) after cycling four times through:

- 4 hours at 158°F (70°C)
- 4 hours at -20°F (-29°C)
- 4 hours at 73°F (22°C)

**Chemical Resistance** – When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids and alkalis.

**Bond Build-up:** The bond strength of 3M™ Adhesive 300 increases as a function of time and temperature

**Temperature/Heat Resistance:** Adhesive 300 is usable for short periods (minutes, hours) at temperatures up to 250°F (120°C) and for intermittent longer periods (days, weeks) up to 150°F (65°C).

**Lower Temperature Service Limit:** -40F (-40°C).

---

## Electrical and Thermal Performance

| Property   |   |
|--|---|
| Dielectric Strength – (500 vac, rms [60 hz/sec])<br>ASTM D149-92 | 340 volts/mil   |
| Dielectric Constant (at 1 KHz)<br>ASTM D150-92                   | 3.21  |
| Dissipation Factor   | 0.040   |
| Coefficient of Thermal Expansion<br>ASTM D696                    | First heat: 20 x 10-5 m/m/°C<br>Second heat: 58 x 10-5 m/m/°C |

**Note:** This data is not for specification purposes. Because of inherent process variability, results may be slightly higher or lower than the typical results listed.

# 3M™ Adhesive Transfer Tapes with Adhesive 300

927 • 950 • 950EK • 9458 • 9471 • 9471PC • 9472 • 9671 • 9672 • 9673 • 9674

---

## Master Width

| Product                       | Master Width |
|-------------------------------|--------------|
| 9458                          | 54"          |
| 927, 9741, 9741PC, 9671, 9673 | 48"          |
| 950, 950EK, 9472, 9672, 9674  | 48"          |

More sizes may be available. Please call 800-223-7427 or talk to your local 3M representative for more information.

---

## Application Techniques

For maximum bond strength (during installation of the final part) the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane (for oily surfaces) or isopropyl alcohol for plastics. Use reagent grade solvents since common household materials like rubbing alcohol frequently contain oils to minimize the drying effect on skin. These oils can interfere with the performance of a pressure-sensitive adhesive.

Consult solvent manufacturers MSDS for proper handling and storage instructions. Also, use disposable wipes that do not contain oils, to remove the cleaning solvents.

It is necessary to provide pressure during lamination (1.5-20 PLI recommended) and during final part installation (10-15 PLI) to allow the adhesive to come into direct contact with the substrate. Using a hard edged plastic tool, which is the full width of the laminated part, helps to provide the necessary pressure at the point of lamination. Heat can increase bond strength when bonding to metal parts (generally this same increase is observed at room temperature over longer times, weeks). For plastic parts, the bond strength is not enhanced with the addition of heat.

The ideal adhesive application temperature range is 70°F (21°C) to 100°F (38°C). Application is not recommended if the surface temperature is below 50°F (10°C) because the adhesive becomes too firm to adhere readily. Once properly applied, at the recommended application temperature, low temperature holding is generally satisfactory (please refer to the Typical Physical Properties and Performance Characteristics section).

When bonding a thin, smooth, flexible material to a smooth surface, it is generally acceptable to use 2 mils of adhesive. If a texture is visible on one or both surfaces, the 5 mil adhesive would be suggested. If both materials are rigid, it may be necessary to use a thicker adhesive to successfully bond the components. 3M™ VHB™ Acrylic Foam Tapes may be required (please refer to data page 70-0709-3863-7).

---

## Application Equipment

To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, Lamination Techniques for Converters of Laminating Adhesives (70-0704-1430-8).

For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

# 3M™ Adhesive Transfer Tapes with Adhesive 300

927 • 950 • 950EK • 9458 • 9471 • 9471PC • 9472 • 9671 • 9672 • 9673 • 9674

---

## Application Ideas

- Long term bonding of graphic nameplates and overlays to surfaces such as metal and low surface energy plastics in the aerospace, medical and industrial equipment, automotive, appliance and electronic markets.
- Bonding metal nameplates and rating plates in the aerospace, medical and industrial equipment, automotive, appliance and electronic markets.
- Lamination to foam for gasket application.

---

## Storage

It is suggested that products are stored at room temperature conditions of 70°F (21°C) and 50% relative humidity.

---

## Shelf Life

If stored properly, product retains its performance and properties for 18 months from date of shipment.

---

## Recognition/ Certification

**TSCA:** This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements

**SDS:** 3M has not prepared a SDS for this product which is not subjected to the SDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R.1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, this product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards.

**UL:** These products have been recognized by Underwriters Laboratories, Inc. under UL 969, Marking and Labeling Systems Materials Component. For more information on the UL Certification, please visit the website at <http://www.3M.com/converter>, select UL Recognized Materials, then select the specific product area.

**Military:** Meets Mil-P 19834B Type 1.

**Note:** One of 3M's core values is to respect our social and physical environment. 3M is committed to comply with ever-changing, global, regulatory and consumer environmental, health, and safety (EHS) requirements. As a service to our customers, 3M is providing information on the regulatory status of many 3M products. Further regulation information including that for OSHA, USCPSI, FDA, California Proposition 65, READY and RoHS, can be found at [3M.com/regs](http://3M.com/regs).

---

## Technical Information

The technical information and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. It has been prepared from testing that was performed using standard test methods, and tested equipment that is calibrated in compliance to ISO9001 and operated by trained professionals in controlled environments. The data should be considered representative or typical only and should not be used for specification purposes. 3M reserves the right to make changes to the design, construction and technical data of products without prior warning.

# 3M™ Adhesive Transfer Tapes with Adhesive 300

927 • 950 • 950EK • 9458 • 9471 • 9471PC • 9472 • 9671 • 9672 • 9673 • 9674

---

## Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluation the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

---

## Warranty, Limited Remedy and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price

---

## Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence, or strict liability.

---

**ISO 9001**

This Industrial Adhesives & Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



---

For more information contact your local 3M representative or call 800-223-7427



### Industrial Adhesives & Tapes Division

#### Converter Markets

3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-223-7427 651-778-4244 (fax)  
[www.3M.com/converter](http://www.3M.com/converter)

3M is a trademark of 3M Company  
© 3M 2016 (6/16)