

BISCO® HT-350

BISCO® HT-350 is a medium firmness silicone foam solution for gasketing and sealing. BISCO HT-350 silicone foam material is designed to offer high sealing capabilities even under low amounts of compression.

PROPERTY	TEST METHOD	TYPICAL VALUE	SPECIFICATION
PHYSICAL			
Color	VISUAL	GRAY/BLACK	---
Thickness Available, mm (inches)		0.80 - 12.70 (1/32 - 1/2) SEE REVERSE	---
Standard Width, mm (inches)	---	914 (36)	---
Density, Kg/m ³ (lb./ft ³)	ASTM D1056	400 (25)	---
CFD Force Measured at 25% Deflection, kPa (PSI)	ASTM D1056	70 (10.1)	41 - 97 (6 - 14)
Tensile, kPa (PSI)	ASTM D412	317 (46)	241 (35) min.
Elongation, %	ASTM D412	64	50% min.
Compression Set, % 22 hours, 100°C (212°F), 50% compression	ASTM D1056	3.7	< 5
Water Absorption, % 24 hours at RT	INTERNAL	1.4	< 5
Flammability	UL94 V-0 UL94 HF-1	Pass Pass	---
Temperature Range	INTERNAL	-55°C to +200°C (-67°F to 392°F)	---
F37 Sealing at 5% compression	ASTM F37	PASS	---

Standard Thickness Tolerance

STANDARD THICKNESS			TOLERANCE	
mm	Inches		mm	Inches
0.8	1/32	0.031	-0.127, +0.381	-0.005, +0.015
1.60	1/16	0.063	±0.508	±0.020
2.39	3/32	0.094	±0.508	±0.020
3.18	1/8	0.125	±0.635	±0.025
4.76	3/16	0.188	±0.635	±0.025
6.35	1/4	0.250	±0.762	±0.030
9.53	3/8	0.375	±1.143	±0.045
12.70	1/2	0.500	±1.27	±0.050

Width Tolerance (Cellular)

NOMINAL WIDTH		TOLERANCE (w/o PSA)		TOLERANCE (with PSA)	
mm	Inches	mm	Inches	mm	Inches
0 < T < 76	0 < T < 3	±1.60	±0.063	±0.787	±0.031
76 < T < 203	3 < T < 8	±2.39	±0.094	±0.787	±0.031
203 < T < 305	8 < T < 12	±3.18	±0.125	±0.787	±0.031
305 < T < 457	12 < T < 18	±4.78	±0.188	±0.787	±0.031
457 < T < 660	18 < T < 26	±5.56	±0.219	±1.600	±0.063
660 < T < 914	26 < T < 36	±6.35	±0.250	±1.600	±0.063

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.



www.marianinc.com
1-800-773-0062



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO, and the BISCO logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2018 Rogers Corporation.

All rights reserved. 0718-PDF • Publication #180-345
www.rogerscorp.com