

## tesa® 4972

### Very thin double-sided filmic tape

tesa® 4972 is a transparent double-sided self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive.

tesa® 4972 features:

- Very thin (only 48µm)
- High adhesion level relative to low thickness
- Excellent resistance to demanding environmental conditions
- Excellent handling performance in converting processes

### Main Application

- Mounting metal or plastic badges and signs
- Fixing reflection foil to LCD frame
- Splicing thin plastic films

### Technical Data

▪ Backing material	PET film	▪ Type of adhesive	tackified acrylic
▪ Color	transparent	▪ Elongation at break	50 %
▪ Total thickness	48 µm 1.9 mils	▪ Tensile strength	20 N/cm 11.4 lbs/in

### Adhesion to

▪ Steel (initial)	7.0 N/cm 64 oz/in	▪ Steel (after 14 days)	9.6 N/cm 87.7 oz/in
▪ ABS (initial)	5.3 N/cm 48.4 oz/in	▪ ABS (after 14 days)	6.5 N/cm 59.4 oz/in
▪ Aluminium (initial)	5.2 N/cm 47.5 oz/in	▪ aluminium (after 14 days)	7.7 N/cm 70.3 oz/in
▪ PC (initial)	6.5 N/cm 59.4 oz/in	▪ PC (after 14 days)	8.6 N/cm 78.6 oz/in
▪ PE (initial)	3.1 N/cm 28.3 oz/in	▪ PE (after 14 days)	3.5 N/cm 32 oz/in
▪ PET (initial)	5.3 N/cm 48.4 oz/in	▪ PET (after 14 days)	7.0 N/cm 64 oz/in
▪ PP (initial)	3.0 N/cm 27.4 oz/in	▪ PP (after 14 days)	4.8 N/cm 43.9 oz/in
▪ PS (initial)	5.4 N/cm 49.3 oz/in	▪ PS (after 14 days)	7.1 N/cm 64.9 oz/in
▪ PVC (initial)	5.7 N/cm 52.1 oz/in	▪ PVC (after 14 days)	9.4 N/cm 85.9 oz/in



www.marianinc.com  
1-800-773-0062

For latest information on this product please visit <http://l.tesa.com/?ip=04972>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



# tesa® 4972

## Very thin double-sided filmic tape

### Properties

▪ Temperature resistance short term	200 °C 392 °F	▪ Resistance to chemicals	● ● ●
▪ Temperature resistance long term	100 °C 212 °F	▪ Softener resistance	● ● ●
▪ Tack	● ●	▪ Static shear resistance at 73,4 °F	● ● ●
▪ Ageing resistance (UV)	● ● ● ●	▪ Static shear resistance at 104 °F	● ●
▪ Humidity resistance	● ● ● ●		

Evaluation across relevant tesa® assortment: ● ● ● ● very good ● ● ● good ● ● medium ● low

### Additional Information

Liner variants:

PV0/PV42 brown glassine paper (71µm; 82g/m<sup>2</sup>)

PV40 white/red tesa® logo glassine paper (71µm; 82g/m<sup>2</sup>)

PV4/PV43 white with blue tesa® logo PE-coated paper (122µm; 120g/m<sup>2</sup>)

PV6 red MOPP-film (80µm; 72g/m<sup>2</sup>)

PV52 transparent PET-film (75µm; 110g/m<sup>2</sup>)

For latest information on this product please visit <http://l.tesa.com/?ip=04972>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.